

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 87303458.1

(51) Int. Cl.³: **C 08 G 77/12**
C 08 G 77/38

(22) Date of filing: 21.04.87

(30) Priority: 28.06.86 GB 8615862

(43) Date of publication of application:
07.01.88 Bulletin 88/1

(84) Designated Contracting States:
BE DE FR GB

(71) Applicant: **Dow Corning Limited**
Inveresk House 1 Aldwych
London WC2R 0HF(GB)

(72) Inventor: **Butler, Derek William**
163 Gladstone Road
Barry South Glamorgan CF6 7YL Wales(GB)

(74) Representative: **Walbeoff, William John**
Dow Corning Limited Cardiff Road Barry
South Glamorgan CF6 7YL Wales(GB)

(54) **Method for making siloxane resins.**

(57) A method for making siloxane resins consisting essentially of tetravalent SiO_2 units and monovalent $\text{R}_3\text{SiO}_{0.5}$ and $\text{H}_a\text{R}_{3-a}\text{SiO}_{0.5}$ units wherein each R denotes an alkyl group or an aryl group having less than 9 carbon atoms and a denotes 1 or 2, comprises reacting in the presence of an acidic catalyst a siloxane resin consisting essentially of $\text{R}_3\text{SiO}_{0.5}$ units and SiO_2 units with $(\text{H}_a\text{R}_{3-a}\text{Si})_2\text{O}$, where R and a are as defined above. Novel resins wherein only 0.1 to 30 percent of the monovalent units have SiH groups are also disclosed.

METHOD FOR MAKING SILOXANE RESINS

This invention is concerned with a method for making siloxane resins containing silicon-bonded hydrogen atoms and with certain novel siloxane resins of this type.

Siloxane resins consisting of triorganosiloxane units
5 ($R_3SiO_{0.5}$) and SiO_2 units are known, commercially available materials and are employed in the formulation of silicone products such as adhesives and antifoams. Such resins are sometimes referred to as MQ resins in view of the presence of the monovalent (M) siloxane units and the quadrivalent
10 or tetravalent (Q) SiO_2 units. Resins of this type wherein the organic groups are alkyl and processes for preparing such resins, are described for example in British Patent Specifications 603 076 and 706 719.

In view of the reactivity of the $\equiv SiH$ group it is
15 sometimes desired to include such groups in resins of the MQ type. British Patent Specification No. 1 418 601 discloses siloxane resins composed of SiO_2 units and units of the general formula $HR_2SiO_{0.5}$ wherein R represents hydrogen or a monovalent hydrocarbon or halohydrocarbon
20 group. Also disclosed in the said Patent Specification is the use of such resins for the manufacture of organopolysiloxane elastomers. In the resins of Specification No. 1 418 601 each of the M units must contain one silicon-bonded hydrogen atom. For certain applications, however,
25 for example when the resins are employed as reactants in chemical synthesis, it is desirable that they contain limited and predetermined amounts of $\equiv SiH$ groups. U.S. Patent Specification No. 3 772 247 discloses organopolysiloxane resins consisting of $R'_3SiO_{0.5}$ units, SiO_2 units
30 and units of the type $HR'SiO$ and/or $HSiO_{1.5}$, in which R' represents a monovalent hydrocarbon group selected from the

group consisting of alkyl, aryl, aralkyl, alkaryl, alkenyl, cycloalkyl or cycloalkenyl groups. Although such resins have $\equiv\text{SiH}$ groups they differ from MQ resins inasmuch as they have a significant content of divalent (HRSiO) and/or
 5 trivalent ($\text{HSiO}_{1.5}$) units.

According to the present invention there is provided a novel method for making siloxane resins consisting essentially of tetravalent SiO_2 units and monovalent $\text{R}_3\text{SiO}_{0.5}$ and $\text{H}_a\text{R}_{3-a}\text{SiO}_{0.5}$ units, wherein each R denotes an alkyl
 10 group or an aryl group having less than 9 carbon atoms, and a denotes 1 or 2, characterised in that it comprises reacting in the presence of an acidic catalyst, a siloxane resin consisting essentially of $\text{R}_3\text{SiO}_{0.5}$ units and SiO_2 units, with $(\text{H}_a\text{R}_{3-a}\text{Si})_2\text{O}$, where R and a are as defined
 15 above.

Siloxane resins consisting essentially of $\text{R}_3\text{SiO}_{0.5}$ units and SiO_2 units wherein R is as defined above suitable for use in the process of the invention are MQ type siloxane resins. Preferably the ratio of monovalent units
 20 (M) to tetravalent units (Q) is in the range of 0.4:1 to 2:1. Suitable siloxane resins for use in the process of this invention may be liquids or solids. For example when R is methyl and the M to Q ratio is above 1:1 the resin is a liquid at ambient temperature, having a viscosity at 25°C
 25 which ranges from about 100 mm²/s for the higher ratios to more than 0.1 m²/s around the 1:1 ratio. When the M to Q ratio drops to below about 1:1 for those resins where R is methyl a solid resin is obtained. Some of these solid resins have a melting point which may be as high as 150°C.
 30 Other resins sublime. Most preferred are MQ resins where the M/Q ratio is in the range of 0.4:1 to 1:1. As stated hereinabove MQ resins are known materials and methods for preparing them have been described, for example, in G.B. Patent Specifications 603 076 and 706 719. MQ resins which

may be used in the process according to the invention may have up to about 5% by weight $\equiv\text{SiOH}$ and/or $\equiv\text{SiOR}$ groups.

According to the method of this invention, the MQ siloxane resins are reacted with disiloxanes of the general formula $(\text{H}_a\text{R}_{3-a}\text{Si})_2\text{O}$, R and a being as defined above. Preferably the disiloxane reactants are those of the formula $(\text{HR}_2\text{Si})_2\text{O}$, those wherein R is methyl being particularly preferred.

The reaction between the siloxane resin and the disiloxane $(\text{H}_a\text{R}_{3-a}\text{Si})_2\text{O}$ is carried out in the presence of an acidic catalyst. Equilibration catalysts, such as trifluoromethane sulphonic acid are particularly useful. Other acidic catalysts, such as for example HCl , H_2SO_4 , supported acid catalysts and paratoluene sulphonic acid will however also work. The catalyst is used in an amount which will range typically from about 0.1 to about 1% by weight based on the weight of the two reagents. The reaction is carried out at elevated temperatures. These temperatures may vary depending on the catalyst used. When for example trifluoromethane sulphonic acid is used as a catalyst, a reaction temperature in the range from 60°C to 90°C is preferably employed. Where high molecular weight solid MQ resins, having a melting point which is higher than the intended reaction temperature, are used a small amount of solvent is preferably added to give a more uniform reaction mixture.

The reaction may generally be carried out by mixing the reagents and the catalyst, and heating the mixture. Following the reaction the catalyst is preferably inactivated, using any suitable technique, for example neutralisation with NaHCO_3 . The reaction may be carried out in the absence of solvent. It may, however, be preferred to use a solvent such as for example toluene, in order to improve the compatibility of the reagents.

5

10

30

The following examples, where all parts and percentages are expressed by weight, unless otherwise indicated, and where Me denotes a methyl group, illustrate the invention.

Preparation of MQ Resins

A first MQ resin was prepared by adding to a flask 129.6g (0.8 mole) hexamethyldisiloxane, 40g hydrochloric acid, 30g absolute ethanol and 60g distilled water. The mixture was agitated and heated to about 70 to 80°C and 208.3g tetraethoxysilane was added dropwise over a period of about 60 minutes. The temperature was increased and maintained at 75 to 80°C for about 30 minutes after completion of the addition. The product was then separated using distilled water and toluene. The toluene/siloxane phase was neutralised and dried over NaHCO_3 and MgSO_4 . The liquor was filtered and the solvent removed under reduced pressure at 130°C. After cooling 172.5g the first MQ resin was recovered (91% of theory). This MQ resin was analysed and had a molecular weight of 881, a viscosity of 554 mm²/s and a ratio of M/Q units of 1.6:1, 0.26 percent residual SiOH and 1.98 percent residual $\text{SiOCH}_2\text{CH}_3$ were found.

A second MQ resin was prepared in the same way except that only 72.9g of hexamethyldisiloxane was added and some toluene was added to aid mobility. 120g of the second MQ resin was obtained having an average ratio of M/Q units of 0.9:1.

A third MQ resin was prepared in the same way as the first except that only 56.7g of hexamethyldisiloxane was used, some toluene was added to aid mobility, the addition and reaction time were extended to 2 hours and the final product was not distilled or analysed.

Example 1

125.8g of the first MQ resin was charged to a 500 cm³ 3-neck flask to which a condenser, agitator and thermocouple were fitted. The flask was previously flushed with nitrogen and had a nitrogen blanket over the mixture. 17.4g of tetramethyldisiloxane (Me_2HSi)₂O was added to the

15

20

25

30

To 120g of the second MQ resin 13.4g of tetramethyldisiloxane was added and the mixture was heated to 60°C, when 0.2g of p-toluene sulphonic acid was added. After

four hours at about 92°C the mixture was cooled to room temperature. The sulphonic acid was neutralised with sodium bicarbonate and filtered out. The reaction product was stripped on a rotary evaporator to 100°C at reduced pressure to remove toluene and volatiles. 89.4g of a gum like material was recovered which was shown by infrared analysis to contain 1.70 percent SiH groups.

Example 4

The third MQ resin was charged to a flask as described in Example 1, together with 6.7g tetramethyldisiloxane. The mixture was heated to 45°C and 0.33g trifluoromethylsulphonic acid was added together with 0.03g of distilled water. The mixture was heated and held at about 97°C for 4 hours after which it was cooled to 60°C and the acid neutralised with dimethylformamide. When the remaining product had cooled to room temperature 20g of NaHCO₃ was added and the mixture filtered to give a crystal clear liquid. This was stripped of volatiles at 100°C to yield 83.5g of a solid resin which was shown by infrared analysis to contain 2.6 percent of SiH.

Example 5

83g of a MQ resin having a M/Q ratio of 1.3:1 was mixed with 13.4g of tetramethyldisiloxane, 0.96g of a supported acid clay catalyst and some toluene to aid the mobility of the mixture. The mixture was heated to reflux at about 100°C for 5 hours. It was then allowed to cool to room temperature and filtered. The clear liquid which was obtained was stripped at 100°C to yield 88.5g of a liquid resin which was shown by infrared to contain 2.52 percent SiH.

CLAIMS

1. A method for making siloxane resins consisting essentially of tetravalent SiO_2 units and monovalent $\text{R}_3\text{SiO}_{0.5}$ and $\text{H}_a\text{R}_{3-a}\text{SiO}_{0.5}$ units, wherein each R denotes an alkyl or an aryl group having less than 9 carbon atoms and a denotes 1 or 2, characterised in that it comprises reacting in the presence of an acidic catalyst a siloxane resin consisting essentially of $\text{R}_3\text{SiO}_{0.5}$ units and SiO_2 units, with $(\text{H}_a\text{R}_{3-a}\text{Si})_2\text{O}$ where R and a are as defined above.
2. A method according to Claim 1 further characterised in that the ratio of monovalent to tetravalent units in the siloxane resin is from 0.4:1 to 2:1.
3. A method according to Claim 2 further characterised in that the ratio of monovalent to tetravalent units is from 0.4:1 to 1:1.
4. A method according to any one of the preceding claims further characterised in that the acidic catalyst is trifluoromethane sulphonic acid.
5. A method according to any one of the preceding claims further characterised in that it is carried out in the presence of a solvent.
6. A method according to any one of the preceding claims further characterised in that R is methyl.
7. A method according to any one of the preceding claims further characterised in that a has a value of 1.

8. A siloxane resin consisting essentially of tetravalent SiO_2 units and monovalent $\text{R}_3\text{SiO}_{0.5}$ and $\text{H}_a\text{R}_{3-a}\text{SiO}_{0.5}$ units wherein each R denotes an alkyl group or an aryl group having less than 9 carbon atoms and a denotes 1 or 2, characterised in that the $\text{H}_a\text{R}_{3-a}\text{SiO}_{0.5}$ units comprise from 0.1% to 30% of the total number of monovalent units present.

0251435

European Patent
Office

EUROPEAN SEARCH REPORT

Application number

EP 87 30 3458

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
P, X	EP-A-0 195 936 (TORAY SILICONE) * page 10, example 4; claim 1 * ---	8	C 08 G 77/12 C 08 G 77/38
A	FR-A-2 203 821 (BAYER) * page 7, line 36 * ---	6, 8	
A	GB-A-2 079 764 (GENERAL ELECTRIC) * claim 6 * -----	8	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 08 G 77/00 C 08 L 83/00
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 27-08-1987	Examiner HOEPFNER W.W.G.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			